

ALKYD RESIN SCSO 261X60

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in xylene : $Z_5 - Z_6 / 100-110$ stock
Color Index	(%60 solution in xylene) Gardner color standard 1933<6
Acid value	DIN 53183 mg koH/g of solid resin < 20
Density	20 ° c (g/ml) approx : 1.12-1.14
Solid %	%60 ± %1
Characteristics	Short Oil, non drying alkyd resin type of oil : linseed soya form of supply : %60 solution in Xylene
Properties	Good compatibility with nitrocellulose and amino resins, very good adhesion to steel and flexibility.
Resin Composition (approx)	%26 OIL (Triglyceride) %40 Phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	✓



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ
İSTANBUL TURKEY
VD.No : 0540441869
Tel:+90 (531) 617 76 55
+90 (212) 812 51 05
Mail : info@alkim.co
www.alkim.co