

ALKYD RESIN SCCO 301X60

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in xylene : $Z_2 - Z_4 / 40-60$ stock
Color Index	(%60 solution in xylene) Gardner color standard 1933:<4
Acid value	DIN 53183(mg koH/ g of solid resin) 6-10
Density	20 ° c (g/ml) approx : 1.1-1.12
Solid %	%60 ± %1
Characteristics	Short Oil, non drying alkyd resin type of oil : soya bean form of supply : %60 solution in xylene
Properties	Excellent build and color retention with amino resins, very good adhesion and excellent gloss,good weather & yellowing resistance and compatibility with nitrocellulose.
Resin Composition (approx)	%30 OIL (Triglyceride) %43 phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	✓



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ
İSTANBUL TURKEY
VD.No : 0540441869
Tel:+90 (531) 617 76 55
+90 (212) 812 51 05
Mail : info@alkim.co
www.alkim.co