

## ALKYD RESIN SCLO 311X60

<b>Viscosity</b>	Gardner Bubble viscometers/25 ° c 60% solution in xylene : Z <sub>5</sub> - Z <sub>7</sub> /110-180 stock
<b>Color Index</b>	(%60 solution in white spirite) Gardner color standard 1933<8
<b>Acid value</b>	DIN 53183 mg koH/g of solid resin<14
<b>Density</b>	20 ° c (g/ml) approx : 1.09-1.11
<b>Solid %</b>	%60 ± %1
<b>Characteristics</b>	Short Oil, air drying alkyd resin Type of oil : tall oil Form of supply : %60 solution
<b>Properties</b>	Rapid and hard through drying, very good resistance to oils and water.
<b>Resin Composition (approx)</b>	%31 OIL (Triglyceride) %34 Phthalic anhydride

### Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ  
İSTANBUL TURKEY  
VD.No : 0540441869  
Tel:+90 (531) 617 76 55  
+90 (212) 812 51 05  
Mail : info@alkim.co  
www.alkim.co