

ALKYD RESIN SCTO 321X60

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in xylene : Z ₆ - Z ₇ /160-200 stock
Color Index	(%60 solution in white spirit) Gardner color standard 1933<7
Acid value	DIN 53183(mg koH/g of solid resin) 8-12
Density	20 ° c (g/ml) approx : 1.08-1.1
Solid %	%60 ± %1
Characteristics	Short Oil, air drying alkyd resin type of oil : tall oil form of supply : %60 solution in xylene
Properties	High viscosity air drying stoving alkyd resin, good compatibility with nitrocellulose and amino resins, good flexibility and adhesion to steel.
Resin Composition (approx)	%32 OIL (Triglyceride) %42 Phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	✓



ALKİM DIŐ TİCARET VE KİMYA SANAYİ LİMİTED ŐİRKETİ
İSTANBUL TURKEY
VD.No : 0540441869
Tel:+90 (531) 617 76 55
+90 (212) 812 51 05
Mail : info@alkim.co
www.alkim.co