

ALKYD RESIN SCSO 331X60

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in xylene : $Z_4 - Z_5 / 60-100$ stock
Color Index	(%60 solution in xylene) Gardner color standard 1933<6
Acid value	DIN 53183 mg koH/g of solid resin : 6-10
Density	20 ° c (g/ml) approx : 1.06-1.08
Solid %	%60 ± %1
Characteristics	Short Oil, air drying alkyd resin type of oil : tall oil form of supply : %60 solution in Xylene
Properties	Excellent color and gloss retention, good compatibility with nitrocellulose and amino resins, very good flexibility.
Resin Composition (approx)	%33 OIL (Triglyceride) %40 Phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ
İSTANBUL TURKEY
VD.No : 0540441869
Tel:+90 (531) 617 76 55
+90 (212) 812 51 05
Mail : info@alkim.co
www.alkim.co