

ALKYD RESIN SCSU 371X60

Viscosity	Gardner Bubble viscometers/25 ° c 60% solution in xylene : Z ₅ - Z ₆ /80-120 stock
Color Index	(%60 solution in xylene) Gardner color standard 1933:<4
Acid value	DIN 53183(mg koH/g of solid resin) 6-10
Density	20 ° c (g/ml) approx : 1.04-1.06
Solid %	%60 ± %1
Characteristics	Short Oil, non drying alkyd resin Type of oil : tall oil Form of supply : %60 solution in xylene
Properties	Good adhesion to steel, good flexibility, excellent color and gloss retention, good compatibility with nitrocellulose and amino resins.
Resin Composition (approx)	%37 OIL (Triglyceride) %38 Phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ
İSTANBUL TURKEY
VD.No : 0540441869
Tel:+90 (531) 617 76 55
+90 (212) 812 51 05
Mail : info@alkim.co
www.alkim.co