

## NC ALCOHOLEATED SEPCIFICATION A30(A400)

TESTS	SPESECIFICATION
Nitrogen Content (%)	10.7 - 11.2
Viscosity (DIN 53179)	400±25CPS
B&J Stability Test in 132 ± 0.2 ° C (ml/gr)	MAX 1.5
Moisture(%)	MAX 4
Damping Medium (Ethanol)	30 ± 5 %
Acidity % (as H2SO4) Dry NC	MAX 0.065

**Measuring viscosity according DIN 53179:**

**Measuring instrument:** Hoeppler viscometer precisin model,ball4 with viscosity solution (see I)

I:For preparation viscosity solution mixing 30% by weight dry solid without plastizier NC A30(A400) with 70% by weight solvent.

(solvent:95% by weight Acetone +5% by weight water )

**Measuring temperature:** 25°c

**Standard range for viscosity according DIN53179:**400cps ± 25cps

**Main Applications :**

Pilishes, polishing lacquers,printing inks,paper lacquers.



ALKİM DIŐ TİCARET VE KİMYA SANAYİ LİMİTED ŐİRKETİ

İSTANBUL TURKEY

VD.No : 0540441869

Tel:+90 (531) 617 76 55

+90 (212) 812 51 05

Mail : info@alkim.co

www.alkim.co