

NC ALCOHOLEATED SEPCIFICATION E27(E400)

TESTS	SPESECIFICATION
Nitrogen Content (%)	11.8-12.2
Viscosity (DIN 53179)	400±25CPS
B&J Stability Test in 132 ± 0.2 ° C (ml/gr)	MAX 1.5
Moisture(%)	MAX 4
Damping Medium (Ethanol)	30 ± 5 %
Acidity % (as H2SO4) Dry NC	MAX 0.065

Measuring viscosity according DIN 53179:

Measuring instrument: Hoeppler viscometer precisin model,ball 4 with viscosity solution (see I).

I. For preparation viscosity solution mixing 27% by weight dry solid without plastizier NC E27(E400) with 73% by weight solvent.

(solvent: 95% by weight Acetone +5% by weight water)

Measuring temperature: 25°c

Standard range for viscosity according DIN53179:400cps ± 25cps

Main Applications :

Wood lacquers, combination lacquers, dipping lacquers,glossy finishing lacquers, dipping lacquers, etc



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ

İSTANBUL TURKEY

VD.No : 0540441869

Tel:+90 (531) 617 76 55

+90 (212) 812 51 05

Mail : info@alkim.co

www.alkim.co