

ALKYD RESIN MCSO 453W55

Viscosity	Gardner Bubble viscometers/25 ° c 55% solution in white spirit/xylene (80/20) : Z ₅ -Z ₆ /100-120 stock
Color Index	(%50 solution in white spirit/xylene) Gardner color standard 1933<6
Acid value	DIN 53183(mg koH/g of solid resin) 6-10
Density	20 ° c (g/ml) approx : 0.96-0.98
Solid %	%55 ± %1
Characteristics	Short Oil, none drying alkyd resin Type of oil : coconut oil Form of supply : %60 solution in xylene
Properties	Oxidizing alkyd resin, excellent color and gloss retention, medium viscosity, good drying hardness.
Resin Composition (approx)	%45 OIL (Triglyceride) %26 phthalic anhydride

Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓		limited



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ
İSTANBUL TURKEY
VD.No : 0540441869
Tel:+90 (531) 617 76 55
+90 (212) 812 51 05
Mail : info@alkim.co
www.alkim.co