

ALKYD RESIN LCSO 603W65

| | |
|---------------------------------------|---|
| Viscosity | Gardner Bubble viscometers/25 ° c 60% solution in white spirit : Z ₂ -Z ₄ /35-70 stock |
| Color Index | (%60 solution in white spirit) Gardner color standard 1933<6 |
| Acid value | DIN 53183(mg koH/g of solid resin) 6-10 |
| Density | 20 ° c (g/ml) approx : 0.92-0.94 |
| Solid % | %65 ± %1 |
| Characteristics | Long Oil, air drying alkyd resin Type of oil : soya bean Form of supply : %65 solution in white spirit |
| Properties | Excellent drying and non yellowing properties.Very good brushability & color retention. Good interior and exterior durability. |
| Resin Composition (approx) | %60 OIL (Triglyceride) %24 phthalic anhydride |

Dilutability

| White spirit | Xylene | Toluene | Acetone | M.I.B.K | Ethylglycol | Butylacetate | N-Butanol |
|--------------|--------|---------|---------|---------|-------------|--------------|-----------|
| ✓ | ✓ | ✓ | ✓ | ✓ | ✓ | ✓ | limited |



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ
İSTANBUL TURKEY
VD.No : 0540441869
Tel:+90 (531) 617 76 55
+90 (212) 812 51 05
Mail : info@alkim.co
www.alkim.co