

## ALKYD RESIN LCSO 603W70

<b>Viscosity</b>	Gardner Bubble viscometers/25 ° c 60% solution in white spirit : Z <sub>2</sub> - Z <sub>4</sub> /30-35-70 stock
<b>Color Index</b>	(%60 solution in white spirit) Gardner color standard 1933<6
<b>Acid value</b>	DIN 53183(mg koH/ g of solid resin) 6-10
<b>Density</b>	20 ° c (g/ml) approx : 0.93-0.95
<b>Solid %</b>	%70 ± %1
<b>Characteristics</b>	Long Oil, air drying alkyd resin Type of oil : soya bean Form of supply : %70 solution in white spirit
<b>Properties</b>	Excellent drying and non yellowing properties.Very good brushability & flow. Good interior and exterior durability.
<b>Resin Composition (approx)</b>	%60 OIL (Triglyceride) %25 phthalic anhydride

### Dilutability

White spirit	Xylene	Toluene	Acetone	M.I.B.K	Ethylglycol	Butylacetate	N-Butanol
✓	✓	✓	✓	✓	✓	✓	limited



ALKİM DIŞ TİCARET VE KİMYA SANAYİ LİMİTED ŞİRKETİ  
İSTANBUL TURKEY  
VD.No : 0540441869  
Tel:+90 (531) 617 76 55  
+90 (212) 812 51 05  
Mail : info@alkim.co  
www.alkim.co