

## ALKYD RESIN ASA 801 X-60

<b>Viscosity</b>	100-150 (ASTM D1545) Gardner bubble Stock viscometers/25
<b>Color Index</b>	Max 5 (ASTM D1544) Gardner
<b>Acid value</b>	<12 (ASTM D1639) mg KOH/g
<b>Density</b>	1.0285 (ASTM D1475) 23 - g/ml
<b>Solid %</b>	60± 1 (ASTM D1259)
<b>Characteristics</b>	Short oil air drying alkyd resin, type of oil: soya bean Form of supply: 60% solution in xylene
<b>Properties</b>	<ul style="list-style-type: none"> <li>• Excellent hardness</li> <li>• Excellent surface and deep drying</li> <li>• Very good adhesion and sanding property</li> <li>• Very good coverage</li> <li>• Very fast drying</li> </ul>
<b>Oil content wt% Approx.</b>	28
<b>Application</b>	<ul style="list-style-type: none"> <li>• Industrial paints and coatings</li> <li>• Hammer finish paints</li> <li>• Fast dry pain</li> </ul>

### Dilutability

White spirit	Xylene	Toluene	Ethyl acetate	Butyl acetate	Acetone	Butanol
Limited	Unlimited	Unlimited	Unlimited	Unlimited	Unlimited	Limited

### Compatibility

Aliphatic poly isocyanate	Medium oil alkyd	Short oil alkyd	Long oil alkyd	Amino resin	Hydroxylated acrylic resin
Compatible	Compatible	Compatible	Incompatible	Incompatible	Incompatible



**Alkim Chemical Industry  
and Foreign Trading, Ltd. Co.**  
No 2/2/4. Mehmetcik Street.  
Barış District. Beylikduzu/Istanbul  
Tel: +90 212 812 5105  
[www.alkim.co](http://www.alkim.co)  
[sales@alkim.co](mailto:sales@alkim.co)