

ALKYD RESIN ASA 804 X-60

| | |
|----------------------------|---|
| Viscosity | 30-60 (ASTM D1545) Gardner bubble Stock viscometers/25 |
| Color Index | Max 4 (ASTM D1544) Gardner |
| Acid value | 4-7 (ASTM D1639) mg KOH/g |
| Density | 1.04 (ASTM D1475) 23 - g/ml |
| Solid % | 60± 1 (ASTM D1259) |
| Characteristics | Short oil alkyd resin type of oil: soya bean Form of supply: 60% solution in xylene |
| Properties | <ul style="list-style-type: none"> • Very fast drying • Good resistance to acidic and basic agent |
| Oil content wt% Approx. | 30±1 |
| Application | <ul style="list-style-type: none"> • Industrial paints and coatings • Hammer finished paints • Fast dry paints |

Dilutability

| White spirit | Xylene | Toluene | Ethyl acetate | Butyl acetate | Acetone | Butanol |
|--------------|-----------|-----------|---------------|---------------|-----------|---------|
| Limited | Unlimited | Unlimited | Unlimited | Unlimited | Unlimited | Limited |

Compatibility

| Aliphatic poly isocyanate | Medium oil alkyd | Short oil alkyd | Long oil alkyd | Amino resin | Hydroxylated acrylic resin |
|---------------------------|------------------|-----------------|----------------|--------------|----------------------------|
| Compatible | Compatible | Compatible | Incompatible | Incompatible | Incompatible |



**Alkim Chemical Industry
and Foreign Trading, Ltd. Co.**
No 2/2/4. Mehmetcik Street.
Barış District. Beylikduzu/Istanbul
Tel: +90 212 812 5105
www.alkim.co
sales@alkim.co